

FIDGLASS UNI 600 HT73®
UNIDIRECTIONAL GLASS FIBER SHEET
FOR STRUCTURAL STRENGTHENING
(600 g/mq)



TECHNICAL GLOBAL SERVICES



Geometrical and Mechanical properties of the FRP composite*

| | |
|---|----------------------|
| Ultimate tensile strength, f_{fk} | 2000 MPa |
| Tensile modulus, E_f | 73 Gpa |
| Ultimate tensile strain, ε_f | 2,74 % |
| Design thickness for the FRP, t_f | 0,240 mm |
| Standard width of the FRP sheet, b_f | 100-200-500 mm |
| Weigth of the dry sheet before impregnation | 600 g/m ² |

* The properties of the composite have been determined according to the UNI and ASTM standards as indicated in the CNR-DT 200/2004 guidelines " Guide for the Design and Construction of Externally Bonded FRP Systems for Strengthening Existing Structures ".

Matrix properties (Resin)

| | |
|---------------------------|------------------------|
| Ultimate tensile strength | 45 MPa |
| Ultimate tensile modulus | 3500 MPa |
| Tensile strain | 1,28 % |
| Density | 1,16 g/cm ³ |
| Mixing ratio | whole package |
| Color | yellow |

MATERIAL CHARACTERISTICS

Description

FIDGLASS UNI 600 HT73 is a unidirectional glass fiber sheet, realized by thermo-welding, process which stops the unwinding of the fiber and which make the installation easier in-situ. It is used on masonry and timber elements for shear, for flexural strengthening.

Ideal for:

- Strengthening vaults, arches and systems-floors, masonry walls;
- Confining columns and piers to increase the compression strength;
- Strengthening due to load increase;
- Seismic mitigation;
- Mitigate design or post-construction defects;
- Strengthening structures which have been modified for architectural or configuration use;
- Control crack propagation and reduce deformations.

Advantages:

- Strengthening system highly is resistant to corrosion;
- High fatigue resistance;
- Lighthweigh and durable;
- Adaptable to complex shapes;
- Adaptable for confinement, shear and flexural strengthening;
- No increase in section of structural elements strengthened;
- Easy to install, after adequate surface preparation.
- Cheaper compared to other strengthening systems.

APPLICATION

1. Surface preparation

Clean the surface from dust, grease and other particles by brushing and sand blasting. Clean the reinforcements from eventual traces of rust and seal possible crevices.

2. Leveling surface

Leveling the surface in order to eliminate eventual roughness and incoherent materials.

3. Primer application

Apply to the surface, with a brush or a roller, a layer of primer and wait until it cured. Level the surface with putty.

4. Application of the first layer of saturant resin

Apply a first layer of epoxy to impregnate the sheet.

5. Sheet installation

Till the epoxy layer is still "fresh", install the sheet previously cut of the required dimension paying attention to not form any bubble by manually smoothing or by passing with a roller.

6. Sheet impregnation

Roll several times the sheet ensuring a good level of impregnation eliminating any excess of resin.

7. Finishing

Apply a second layer of epoxy and finish by applying silica sand; proceed with the application of polyuretan paint or polyurea for protecting the reinforcement.

Registered Office FIDIA S.r.l. Via Gerardo Dottori, n.85 06132 S. Sisto PERUGIA
 Tel.+39-075-5271550 - Fax.+39-075-5298077
 Part. IVA 02140130549 C.C.I.A.A. 181644 Iscr. Trib. PG 28053

Head Office Via Y. Gagarin, n. 61/63 06070 San Mariano – PERUGIA Tel.+39-075-5170096 - Fax.+39-075-5177546
 Piazza Duomo, n.17 20121 Milano Tel.+39-02-72093424 – Fax.+39-02-45471830

Web-Site: www.fidiaglobalservice.com - E-mail: info@fidiaglobalservice.com

FIDGLASS UNI 600 HT73®
UNIDIRECTIONAL GLASS FIBER SHEET
FOR STRUCTURAL STRENGTHENING
(600 g/mq)



TECHNICAL GLOBAL SERVICES

PACKAGES

Each job size, sheets can be supplied to meet design requirements in different widths and lengths. Standard widths available in stock are 100, 200, 300, 400, 500 mm and different lengths.

RECOMMENDATIONS

When managing the sheet, protective clothing and glasses must be worn and instructions regarding the installation of the materials must be followed carefully.

Inhalation: breath fresh air and rinse out your mouth.

Skin contact: no special measures are needed.

Contact with eyes: rinse for at least 15 minutes; in case of use of contact lenses they must be removed and rinsed for at least another 5/10 minutes; If still painful seek medical care.

Ingestion: rinse the mouth by drinking water and inducing vomit. Seek medical care.

Yard storage: Keep in a dry covered area which is far from substances which may jeopardize the optimal bond of the matrix.

APPLICATION EXAMPLES

To learn about structural projects using unidirectional glass fiber sheet visit the "Application" area at FIDIA website: www.fidiaglobalservice.com.

QUALITY & CERTIFICATION

Material supply is accompanied by a certificate of origin of the material from the producer and the certificate of characterization of the mechanical properties issued by an Italian laboratory approved by the Ministry of Infrastructure and Transport according to Art. 59 of D. P. R. 380/2001 construction material sector following the law .1086/71, with Decree n.38194 of 14/01/1992 and followings.

LEGAL NOTES

The technical advice that Fidia S. r.l. Technical Global Services provides, orally or in writing, as assistance to the customer or installer on the basis of its experiences, corresponding to current scientific knowledge and practices, are not binding and do not demonstrate any legal or contractual obligation accessory with contract of sale. They do not exempt from liability buyer feel our products as regards their suitability for use. For the rest are valid our commercial conditions. Discrepancies that original content and/or use not involve any responsibility by the company's Fidia S. r.l.. The Client is obliged to check that this report, and the values are valid for the consignment of product of its interest and not be overcome, as replaced by subsequent editions and/or new formulations of the product. In doubt, please contact advance our Technical Office.

Registered Office FIDIA S.r.l. Via Gerardo Dottori, n.85 06132 S. Sisto PERUGIA
Tel.+39-075-5271550 - Fax.+39-075-5298077
Part. IVA 02140130549 C.C.I.A.A. 181644 Iscr. Trib. PG 28053

Head Office Via Y. Gagarin, n. 61/63 06070 San Mariano – PERUGIA Tel.+39-075-5170096 - Fax.+39-075-5177546
Piazza Duomo, n.17 20121 Milano Tel.+39-02-72093424 – Fax.+39-02-45471830

Web-Site: www.fidiaglobalservice.com - E-mail: info@fidiaglobalservice.com